

2. INSTRUMENTATION AND SAMPLE PREPARATION

hence to increase the attainable pressure, which is inversely proportional to the chamber diameter;

- (v) The microbeam can illuminate a small selected portion of the sample chosen for the investigation, which can be used to perform single-crystal diffraction on a selected grain or for X-ray tomography of the sample and its inclusions;
- (vi) The beam diameter is smaller than the diameter of the chamber, which minimizes or even eliminates the effects of beam shadowing;
- (vii) The X-ray wavelength is tuneable down to about 0.3 Å. This considerably increases the data completeness and reduces absorption effects in the sample and DAC.

Owing to these features, synchrotron beams are ideally suited for high-pressure diffraction experiments and some researchers have completely stopped using in-house laboratory equipment with sealed X-ray tubes. Historically, the first use of synchrotron radiation for high-pressure studies was reported by Buras, Olsen & Gerward (1977) and Buras, Olsen, Gerward *et al.* (1977). Conventional diffractometers with sealed X-ray tubes can be effectively used for preliminary powder diffraction experiments. For example, a new high-pressure phase of (+)-sucrose was found in this way (Patyk *et al.*, 2012), although the data were insufficient for any structural refinements.

Diffraction data are collected in single and multiple exposures, and the pressure is controlled remotely by inflating a membrane through a gas system. Currently assembled high-pressure powder diffraction synchrotron beamlines incorporate on-line pressure calibration using ruby fluorescence and, often, Raman spectroscopy.

2.7.10. Sample preparation

Several basic techniques can be used to prepare a sample for a high-pressure experiment, for example:

- (i) A solid sample can be mounted under ambient conditions in the high-pressure chamber together with the hydrostatic fluid, then sealed and pressurized;
- (ii) A solid sample can be mounted under ambient conditions in the high-pressure chamber, condensed gas loaded at elevated pressure (Tkacz, 1995; Rivers *et al.*, 2008; Couzinet *et al.*, 2003; Mills *et al.*, 1980; Yagi *et al.*, 1996; Kenichi *et al.*, 2001) or under cryogenic conditions, and the sample sealed and further pressurized by gasket compression;
- (iii) A liquid sample can fill the whole chamber volume under ambient conditions, or condensed gases or their mixtures can be loaded at elevated pressure, and after sealing the DAC the sample is frozen under isothermal conditions;
- (iv) A crystal of the pure compound or of a solvate can precipitate from the mixture (solution) when compressed isothermally – the crystal can be in the form of a single crystal or a powder, fully or partly filling the DAC chamber;
- (v) Samples completely filling the DAC chamber can be compressed isothermally or undergo isochoric treatment, but strains can be generated in a single crystal or in the grains of a compressed powder conglomerate by anisotropic thermal contraction/expansion; this strain can be avoided by having an excess of the hydrostatic component of the mixture;
- (vi) A solid powdered sample can be mixed with a powder of another compound, which is much softer than the sample and is used as a pseudo-hydrostatic medium (halite and MgO are often used for this purpose) – this technique is mainly used for cubic or isotropic samples in large-volume

presses, where (pseudo)isotropic strain and pseudo-spherical compression minimize the effect of preferential orientation in the sample.

Preferential orientation can significantly hamper the quality of powder diffraction data, and corrections for this effect should be applied in the Rietveld refinement. All Rietveld refinement programs include preferential orientation models, which fit the data with satisfactory results (McMahon, 2004, 2005; Filinchuk, 2010).

2.7.11. Hydrostatic conditions

Hydrostatic conditions in the sample chamber are essential for good-quality high-pressure diffraction data. They are equally important for single-crystal and powder diffraction experiments. To secure hydrostaticity, the sample is submerged in a hydrostatic medium. The pressure and temperature ranges of the planned experiment depend on the hydrostatic properties of the applied medium. Eventually all substances solidify because of crystallization or vitrification (Piermarini *et al.*, 1973; Eggert *et al.*, 1992; Grocholski & Jeanloz, 2005), which can lead to damage of single crystals, anisotropic strain in powder grains and inhomogeneity of pressure across the sample. It is also important to protect a solid sample from dissolution in the hydrostatic fluid. The dissolved sample can lose its required features (such as shape, polymorphic form or chemical composition) and recrystallize at higher pressure in an undesired form. For example, a fine powder may recrystallize into a few large and preferentially oriented grains. Another potential problem can arise from reactions between the sample and the hydrostatic medium. For example, a pure compound can form solvates incorporating molecules of the hydrostatic fluid (Olejniczak & Katrusiak, 2010, 2011; Andrzejewski *et al.*, 2011; Tomkowiak *et al.*, 2013; Boldyreva *et al.*, 2002; Fabbiani & Pulham, 2006). This has also been observed for helium and argon penetrating into the structures of the fullerenes C₆₀ and C₇₀ (Samara *et al.*, 1993) and into arsenolite As₄O₆ (Guńka *et al.*, 2015). High-pressure crystallization of water in the presence of helium leads to an inclusion compound interpreted as ice XII. Therefore, the hydrostatic medium should be carefully chosen for a specific experiment, depending on the sample solubility, the pressure range and the type of investigation, whether a mounted-sample study, or *in situ* crystallization or reaction (Sobczak *et al.*, 2018; Pórolniczak *et al.*, 2018).

Many minerals and inorganic samples hardly dissolve at all and a commonly applied pressure-transmitting medium is a mixture of methanol, ethanol and water (16:3:1 by volume), hydrostatic to over 10 GPa at 296 K (see Table 2.7.1); separately, pure methanol crystallizes at 3.5 GPa, ethanol at 1.8 GPa and water at 1.0 GPa. If a sample dissolves well in methanol, ethanol and water, other fluids can be selected (Piermarini *et al.*, 1973; Angel *et al.*, 2007). Liquids like glycerine (hydrostatic to 3 GPa) and special inert fluids, such as silicone oil (Shen *et al.*, 2004; Ragan *et al.*, 1996), Daphne oil (Yokogawa *et al.*, 2007; Murata *et al.*, 2008; Klotz *et al.*, 2009), or condensed gases, like helium, argon and hydrogen (Tkacz, 1995; Dewaele & Loubeyre, 2007), can be used. Alternatively, a saturated solution of the sample compound, for example in a methanol–ethanol–water mixture, can prevent sample dissolution, but on increasing the pressure the compound can precipitate in the form of a powder or single crystals. One can choose to load an excess of the sample into the chamber before filling it up with the hydrostatic fluid, which would dissolve only some of the sample.